

IN THE SPECIFICATION

Please replace paragraph [0012] with the following rewritten paragraph:

ai [0012] To limit alkali mobility, the molar ratio of ~~Na₂/K₂O~~ Na₂O/K₂O is preferably approximately 1.0. However, a molar ratio of 1.2-3.0 is preferred in order to minimize liquidus temperature. The alkalis are used to maintain a high coefficient of thermal expansion (CTE). CaO and MgO limit alkali mobility and flux of the melt at relatively high temperatures while helping to maintain a high strain point. The higher atomic weight cations, such as Ba²⁺ or La³⁺, increase the density of the glass. B₂O₃ generally lowers the viscosity of the glass and improves liquidus temperature. B₂O₃ also lowers the strain point and CTE of the glass.

NOT AVAILABLE COPY